



FULLY BLEACHED LINER



PM6



100% virgin fiber



MANUFACTURED: Ilim Group, Koryazhma Branch

PROPERTY	VALUE									
Grammage, (ISO 536), g/m ²	100 ± 2	110 ± 2	115 ± 2	120 ± 2	135 ± 2	150 ± 2	160 ± 2	170 ± 2	200 ± 2	
Moisture, %, (ISO 287), min/max	6 – 8									
Cobb test 60, g/m ² (ISO 535), max	30									
SCT CD, kN/m, (ISO 9895)										
Guaranteed min	1,40	1,55	1,75	1,80	2,10	2,20	2,30	2,40	2,50	
Average	1,45	1,60	1,80	1,90	2,20	2,30	2,40	2,50	2,55	
Bursting Strength, kPa, (ISO 2758)										
Guaranteed min	300	320	330	340	355	385	395	410	430	
Average	340	360	370	375	380	410	420	435	450	
Brightness, %, min (ISO 2470)	80									
Dennison, max (ISO 15137)	16									
Smoothness Bekk, sec, min (ISO 5627)	30 – 50									

Test climate (ISO 187) Temperature (23 ± 1) °C, relative humidity (50 ± 2) %



COMPOSITION:

SW pulp, HW pulp



SPECIFICATION DATE:

19.06.2020