



# FULLY BLEACHED LINER

## PM7



100% virgin fiber



**MANUFACTURED:** Ilim Group, Koryazhma Branch

PROPERTY	VALUE				
Grammage, (ISO 536), g/m <sup>2</sup>	<b>100 +1/-3</b>	<b>110 +1/-3</b>	<b>115 +1/-3</b>	<b>120 +1/-3</b>	<b>135 /-3</b>
Moisture, %, (ISO 287), min/max	6 – 8				
Cobb test 60, g/m <sup>2</sup> (ISO 535), max	30				
SCT CD, kN/m, (ISO 9895)					
Guaranteed min	1,70	1,80	1,90	2,00	2,10
Average	1,80	1,90	2,00	2,20	2,30
Bursting Strength, kPa, (ISO 2758)					
Guaranteed min	340	360	370	380	390
Average	370	380	400	410	430
Brightness, %, min (ISO 2470)	82				
Dennison, max (ISO 15137)	16				
Smoothness Bekk, sec, min (ISO 5627)	40				

Test climate (ISO 187) Temperature (23 ± 1) °C, relative humidity (50 ± 2) %



### COMPOSITION:

SW pulp, HW pulp



### SPECIFICATION DATE:

19.06.2020